

## Material - ASTM A 182 F1925N

**Standard Specification for Forged or Rolled Alloy and Stainless Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High-Temperature Service**

**Group - Non-Ferrous Nickel Alloys**

**Sub Group - ASTM A 182 F1925N Forged or Rolled Alloy and Stainless Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High-Temperature Service**

**Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries**

**Grade Belongs to the Industry - Pipe Flanges, Forged Fittings and Valve**

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	19.000 - 21.000		
Sulphur	S %	0.010 max.		
Molybdenum	Mo %	6.000 - 7.000		
Phosphorus	P %	0.030 max.		
Copper	Cu %	0.500 - 1.500		
Nitrogen	N %	0.150 - 0.250	Mechanical Properties	
Nickel	Ni %	24.000 - 26.000	Tensile Strength in Mpa	650 min.
Iron	Fe %	Balance	Yield Strength in Mpa	295 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 649 N08926	ASTM	USA	Bar and Wire
B 472 N08926	ASTM	USA	Billets and Bars
B 625 N08926	ASTM	USA	Plate, Sheet and Strip
B 673 N08926	ASTM	USA	Pipe
B 674 N08926	ASTM	USA	Tube
B 677 N08926	ASTM	USA	Pipe and Tube
SB-625 N08926	ASME	USA	Plate, Sheet and Strip

**For any further inquiries, please do not hesitate to contact us. You may visit our website at [AMTECH TECHNOCAST PVT. LTD.](http://AMTECH TECHNOCAST PVT. LTD.), call us at [+91 9879817994](tel:+919879817994), or email us at [manish@amtechtechnocast.com](mailto:manish@amtechtechnocast.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.