

Material - ASTM A 216 Grade WCC

Standard Specification for Steel Castings, Carbon, Suitable for Fusion for High-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 216 Grade WCC Steel Castings, Carbon, Suitable for Fusion for High-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.200 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.500 max.		
Molybdenum	Mo %	0.200 max.		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.030 max.	Tensile Strength in Mpa	485 - 655
Other	Ot %	1.000 max.	Yield Strength in Mpa	275 min.
Niobium	Nb %	0.020 max.	Elongation in %	22 min.
Iron	Fe %	Balance	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 GP280GH	BS	British	Plate, Tubes and Forging
SCPH 2	JIS	Japan	Plate, Tubes and Forging
SCPL 1	JIS	Japan	Plate, Tubes and Forging
GP 280 GH	DIN	Germany	Plate, Tubes and Forging
GP 280 GH	MSZ	Hungary	Plate, Tubes and Forging
GP 280 GH	UNI	Italy	Plate, Tubes and Forging
GP 280 GH	UNE	Spain	Plate, Tubes and Forging

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.