

Material - ASTM A 217 Grade WC9

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 217 Grade WC9 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.180	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	2.000 - 2.750		
Molybdenum	Mo %	0.900 - 1.200		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.500 max.		
Tungsten	W %	0.100 max.		
Other	Ot %	1.000 max.	Mechanical Properties Tensile Strength in Mpa 485 - 655 Yield Strength in Mpa 275 min. Elongation in % 20 min. Reduction of Area in % 35 min. Hardness in HB - Impact in Joule -	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G17CrMo9-10	BS	British	Plate, Tubes and Forging
G17CrMo9-10	ISO	International	Casting
1.7379	ISO	International	Casting
15 CD9.10-M	AFNOR NF	France	Pump, Valve and Fitting
SCPH 32	JIS	Japan	Casting
A 217 J21890	ASTM	USA	Casting
SCPH 32-CF	JIS	Japan	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.