

Material - ASTM A 494 CY5SnBiM

Standard Specification for Castings, Nickel and Nickel Alloy

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM A 494 CY5SnBiM Castings, Nickel and Nickel Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	11.000 - 14.000		
Bismuth	Bi %	3.000 - 5.000		
Molybdenum	Mo %	2.000 - 3.500		
Tin	Sn %	3.000 - 5.000	Mechanical Properties	
Iron	Fe %	2.000 max.	Tensile Strength in Mpa	330 min.
Nickel	Ni %	Balance	Yield Strength in Mpa	230 min.
-	-	-	Elongation in %	9 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	140 - 150
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-494 CYSSnBiM	ASME	USA	Casting
N26055	UNS	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.