

## Material - ASTM A 505 8630

**Standard Specification for Alloy Steel, Sheet, Strip, Hot-Rolled and Cold-Rolled**

**Group - Ferrous Mild Steel Alloys**

**Sub Group - ASTM A 505 8630 Alloy Steel, Sheet, Strip, Hot-Rolled and Cold-Rolled**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Bar, Wire, Tube and Forging**

| Chemical Composition |      |               | Heat Treatment                                                |   |
|----------------------|------|---------------|---------------------------------------------------------------|---|
| Carbon               | C %  | 0.280 - 0.330 | As- Cast or Normalising or Annealing or Hardening + Tempering |   |
| Silicon              | Si % | 0.150 - 0.300 |                                                               |   |
| Manganese            | Mn % | 0.700 - 0.900 |                                                               |   |
| Phosphorus           | P %  | 0.040 max.    |                                                               |   |
| Sulphur              | S %  | 0.040 max.    |                                                               |   |
| Chromium             | Cr % | 0.400 - 0.600 |                                                               |   |
| Molybdenum           | Mo % | 0.150 - 0.250 |                                                               |   |
| Nickel               | Ni % | 0.400 - 0.700 |                                                               |   |
| Iron                 | Fe % | Balance       |                                                               |   |
| -                    | -    | -             | Mechanical Properties                                         |   |
| -                    | -    | -             | Tensile Strength in Mpa                                       | - |
| -                    | -    | -             | Yield Strength in Mpa                                         | - |
| -                    | -    | -             | Elongation in %                                               | - |
| -                    | -    | -             | Reduction of Area in %                                        | - |
| -                    | -    | -             | Hardness in BHN                                               | - |
| -                    | -    | -             | Impact in Joule                                               | - |

| Cross Reference Table |          |           |                              |
|-----------------------|----------|-----------|------------------------------|
| Material              | Standard | Country   | Grade Belong to the Industry |
| A915 Grade SC 8630    | UNS      | USA       | Casting                      |
| J13095                | UNS      | USA       | Bar, Wire, Tube and Forging  |
| A 29 8630             | ASTM     | USA       | Bar, Wire, Tube and Forging  |
| 8630                  | AISI     | USA       | Bar, Wire, Tube and Forging  |
| 8630                  | SAE      | USA       | Bar, Wire, Tube and Forging  |
| 8630                  | AMS      | USA       | Bar, Wire, Tube and Forging  |
| 8630                  | AS       | Australia | Bar, Wire, Tube and Forging  |

**For any further inquiries, please do not hesitate to contact us. You may visit our website at [AMTECH TECHNOCAST PVT. LTD.](http://AMTECH TECHNOCAST PVT. LTD.), call us at [+91 9879817994](tel:+919879817994), or email us at [manish@amtechtechnocast.com](mailto:manish@amtechtechnocast.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.