

Material - ASTM A 510 1030

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 150 1030 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod and Round Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Wire Rod and Round Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.280 - 0.340	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	B %	0.0008 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 415 - 896 Yield Strength in Mpa 260 min. Elongation in % 5 min. Reduction of Area in % 35 - 42 Hardness in HB 137 - 149 Impact in Joule 36.9 - 52.3 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10300	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1030	SAE	USA	Steel
1030	AISI	USA	Tubing
A 1040 1030	ASTM	USA	Steel
A 108 Grade 1030	ASTM	USA	Steel and Bar
A 29 1030	ASTM	USA	Steel and Bar
A 512 Grade 1030	ASTM	USA	Tubing

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.