

Material - ASTM A 510 1146

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Wire and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 1146 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Wire and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Wire Rod, Round Wire and Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.420 - 0.490	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.080 - 0.130		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 590 - 650 Yield Strength in Mpa 320 min. Elongation in % 12 min. Reduction of Area in % 35 - 40 Hardness in HB 170 - 187 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G11460	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1146	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1146	AISI	USA	Steel and Bar
A 1040 1146	ASTM	USA	Steel
A 29 1146	ASTM	USA	Steel and Bar
A 576 11L46	ASTM	USA	Steel and Bar
A 576 1146	ASTM	USA	Steel and Bar

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.