

Material - ASTM A 510 12L14

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Wire and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 510 12L14 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Wire Rod, Round Wire and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Wire Rod, Round Wire and Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.850 - 1.150		
Phosphorus	P %	0.040 - 0.090		
Sulphur	S %	0.260 - 0.350		
Lead	Pb %	0.150 - 0.350		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 390 - 540 Yield Strength in Mpa 230 min. Elongation in % 10 min. Reduction of Area in % 35 - 45 Hardness in HB 121 - 163 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G12140	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
12L14	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
12L14	AISI	USA	Steel and Bar
A 1040 12L14	ASTM	USA	Steel
SA-29 12L14	ASME	USA	Steel
A 519 12L14	ASTM	USA	Tubing
A 576 12L14	ASTM	USA	Steel and Bar

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.