

Material - ASTM A 567 Grade 1

Standard Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application and Cobalt alloy for High Strength at Elevated Temperatures

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM A 567 Grade 1 Castings, Investment, Carbon and Low Alloy Steel for General Application and Cobalt alloy for High Strength at Elevated Temperatures

Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.300	As-Cast or Annealing or Age Hardning	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	25.000 - 29.000		
Sulphur	S %	0.040 max.		
Molybdenum	Mo %	5.000 - 6.000		
Phosphorus	P %	0.040 max.		
Boron	B %	0.007 max.	Mechanical Properties Tensile Strength in Mpa 360 min. Yield Strength in Mpa - Elongation in % 10 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Iron	Fe %	3.000 max.		
Nickel	Ni %	1.750 - 3.750		
Cobalt	Co %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 732 Grade 21	ASTM	USA	Casting
5385	SAE	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.