

Material - ASTM A 576 10L80

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 576 10L80 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.750 - 0.880	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Boron	B %	0.0008 max.		
Copper	Cu %	0.200 min.		
Lead	Pb %	0.150 - .350		
Silicon	Si %	0.100 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	680 - 2310
-	-	-	Yield Strength in Mpa	420 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	25 - 40
-	-	-	Hardness in HB	192 - 229
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10800	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1080	SAE	USA	Steel
1080	AISI	USA	Steel and Bar
A 1040 1080	ASTM	USA	Steel
A 29 1080	ASTM	USA	Steel and Bar
A 510 1080	ASTM	USA	Wire Rods, Round Wire and Steel
A 682 G10800	ASTM	USA	Steel and Strip

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.