

Material - ASTM A 713 Grade 1566

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Wire

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 713 Grade 1566 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.600 - 0.710	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.850 - 1.150		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Silicon	Si %	0.100 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 1960 - 2240 Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15660	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1566	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1566	AISI	USA	Steel and Bar
A 29 1566	ASTM	USA	Steel and Bar
A 510 1566	ASTM	USA	Wire Rod, Round Wire and Steel
A 576 15L66	ASTM	USA	Steel and Bar
A 713 G15660	ASTM	USA	Steel and Wire

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.