

Material - ASTM A 743 Grade CN-7M

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 743 Grade CN-7M Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	19.000 - 22.000		
Molybdenum	Mo %	2.000 - 3.000		
Nickel	Ni %	27.500 - 30.500		
Copper	Cu %	3.000 - 4.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	425 min.
			Yield Strength in Mpa	170 min.
			Elongation in %	35 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
332C11	BS	British	Casting
Z 2 NCDU 25.20.04 M	AFNOR NF	France	Casting
2074/H9A	AS	Australia	Casting
A 351 Grade CN7M	ASTM	USA	Casting
A 743 N08007	ASTM	USA	Casting
A 744 Grade CN-7M	ASTM	USA	Casting
SA-351 Grade CN7M	ASME	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.