

## Material - ASTM A 815 S32760

**Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications**

**Group - Ferrous Stainless Steel Alloys**

**Sub Group - ASTM A 815 S32760 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Steel and Pipe**

| Chemical Composition |      |                 | Heat Treatment          |          |
|----------------------|------|-----------------|-------------------------|----------|
| Carbon               | C %  | 0.030 max.      | Solution Annealing      |          |
| Silicon              | Si % | 1.000 max.      |                         |          |
| Manganese            | Mn % | 1.000 max.      |                         |          |
| Phosphorus           | P %  | 0.030 max.      |                         |          |
| Sulphur              | S %  | 0.010 max.      |                         |          |
| Chromium             | Cr % | 24.000 - 26.000 |                         |          |
| Nickel               | Ni % | 6.000 - 8.00    |                         |          |
| Molybdenum           | Mo % | 3.000 - 4.000   |                         |          |
| Nitrogen             | N %  | 0.200 - 0.300   | Mechanical Properties   |          |
| Copper               | Cu % | 0.500 - 1.000   | Tensile Strength in Mpa | 750 min. |
| Tungsten             | W %  | 0.500 - 1.000   | Yield Strength in Mpa   | 550 min. |
| Iron                 | Fe % | Balance         | Elongation in %         | 25 min.  |
| -                    | -    | -               | Reduction of Area in %  | -        |
| -                    | -    | -               | Hardness in HB          | 310 max. |
| -                    | -    | -               | Impact in Joule         | -        |

| Cross Reference Table |          |         |                               |
|-----------------------|----------|---------|-------------------------------|
| Material              | Standard | Country | Grade Belong to the Industry  |
| A240 UNS S32760       | ASTM     | USA     | Steel, Plate, Sheet and Strip |
| S32760                | UNS      | USA     | Steel                         |
| A276 S32760           | ASTM     | USA     | Steel, Bar and Shapes         |
| A789 S32760           | ASTM     | USA     | Steel and Tube                |
| A790 S32760           | ASTM     | USA     | Steel and Pipe                |
| A959 S32760           | ASTM     | USA     | Steel                         |
| A988 S32760           | ASTM     | USA     | Steel                         |

**For any further inquiries, please do not hesitate to contact us. You may visit our website at [AMTECH TECHNOCAST PVT. LTD.](http://AMTECH TECHNOCAST PVT. LTD.), call us at [+91 9879817994](tel:+919879817994), or email us at [manish@amtechtechnocast.com](mailto:manish@amtechtechnocast.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.