

Material - ASTM A 830 1046

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 830 1046 Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.430 - 0.500	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.150 - 0.400		
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 590 - 650 Yield Strength in Mpa 320 min. Elongation in % 12 min. Reduction of Area in % 35 - 45 Hardness in BHN 170 - 187 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AW2	BS	British	Casting
1046	SAE	USA	Casting
1046	AISI	USA	Casting
A 1040 1046	ASTM	USA	Casting
A 29 1046	ASTM	USA	Casting
A 510 1046	ASTM	USA	Casting
A 576 1046	ASTM	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.