

Material - ASTM A 915 Grade SC 8630

Standard Specification for Steel Castings, Carbon and Alloy, Chemical Requirements Similar to Standard

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 915 Grade SC 8630 Steel Castings, Carbon and Alloy, Chemical Requirements Similar to

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.280 - 0.330	As- Cast or Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	0.600 - 1.000		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.400 - 0.600		
Molybdenum	Mo %	0.150 - 0.250		
Nickel	Ni %	0.400 - 0.700	Mechanical Properties Tensile Strength in Mpa 610 min. Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J13095	UNS	USA	Casting
8630	AISI	USA	Bar, Wire, Tube and Forging
8630	SAE	USA	Bar, Wire, Tube and Forging
8630	AS	Australia	Bar, Wire, Tube and Forging
8630	AMS	USA	Bar, Wire, Tube and Forging
A 29 8630	ASTM	USA	Bar, Wire, Tube and Forging
A 505 8630	ASTM	USA	Bar, Wire, Tube and Forging

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.