

Material - ASTM A 959 S30600

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A959 S30600 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.018 max.	Solution Annealing	
Silicon	Si %	3.700 - 4.300		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	17.000 - 18.500		
Molybdenum	Mo %	0.200 max.		
Nickel	Ni %	14.000 - 15.500		
Copper	Cu %	0.500 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	540 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S30600	ASTM	USA	Steel, Plate, Sheet and Strip
A167 S30600	ASTM	USA	Steel, Plate, Sheet and Strip
A959 S30600	ASTM	USA	Steel
A269 S30600	ASTM	USA	Steel and Tube
A312 S30600	ASTM	USA	Steel and Pipe
A358 S30600	ASTM	USA	Steel and Pipe
A479 S30600	ASTM	USA	Steel and Bar

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.