

## Material - ASTM A 959 S43940

**Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications**

**Group - Ferrous Stainless Steel Alloys**

**Sub Group - ASTM A 959 S43940 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Steel**

| Chemical Composition |      |                 | Heat Treatment                     |          |
|----------------------|------|-----------------|------------------------------------|----------|
| Carbon               | C %  | 0.030 max.      | Annealing or Hardening + Tempering |          |
| Silicon              | Si % | 1.000 max.      |                                    |          |
| Manganese            | Mn % | 1.000 max.      |                                    |          |
| Phosphorus           | P %  | 0.040 max.      |                                    |          |
| Sulphur              | S %  | 0.015 max.      |                                    |          |
| Chromium             | Cr % | 17.500 - 18.500 |                                    |          |
| Titanium             | Ti % | 0.100 - 0.600   |                                    |          |
| Niobium              | Nb % | 0.300 max.      |                                    |          |
| Iron                 | Fe % | Balance         | Mechanical Properties              |          |
| -                    | -    | -               | Tensile Strength in Mpa            | 430 min. |
| -                    | -    | -               | Yield Strength in Mpa              | 205 min. |
| -                    | -    | -               | Elongation in %                    | 18 min.  |
| -                    | -    | -               | Reduction of Area in %             | -        |
| -                    | -    | -               | Hardness in HB                     | 180 max. |
| -                    | -    | -               | Impact in Joule                    | -        |

| Cross Reference Table |          |         |                               |
|-----------------------|----------|---------|-------------------------------|
| Material              | Standard | Country | Grade Belong to the Industry  |
| A240 UNS S43932       | ASTM     | USA     | Steel, Plate, Sheet and Strip |
| S43932                | UNS      | USA     | Steel                         |
| A959 S43932           | ASTM     | USA     | Steel                         |
| S43940                | UNS      | USA     | Steel                         |
| A240 UNS S43940       | ASTM     | USA     | Steel, Sheet, Plate and Strip |
| A268 S43940           | ASTM     | USA     | Steel and Tube                |
| -                     | -        | -       | -                             |

**For any further inquiries, please do not hesitate to contact us. You may visit our website at [AMTECH TECHNOCAST PVT. LTD.](http://AMTECH TECHNOCAST PVT. LTD.), call us at [+91 9879817994](tel:+919879817994), or email us at [manish@amtechtechnocast.com](mailto:manish@amtechtechnocast.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.