

Material - ASTM A 959 Type 25-4-4

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 959 Type 25-4-4 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	Annealing or Hardening + Tempering	
Silicon	Si %	0.750 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	24.500 - 26.000		
Molybdenum	Mo %	3.500 - 4.500		
Nickel	Ni %	3.500 - 4.500	Mechanical Properties Tensile Strength in Mpa 620 min. Yield Strength in Mpa 515 min. Elongation in % 20 min. Reduction of Area in % - Hardness in HB 270 max. Impact in Joule -	
Nitrogen	N %	0.035 max.		
Titanium	Ti %	0.800 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S44635	ASTM	USA	Steel, Plate, Sheet and Strip
S11635	UNS	USA	Steel
A176 S44635	ASTM	USA	Steel, Sheet, Plate and Strip
SA-240 UNS S44635	ASME	USA	Steel
A268 25-4-4	ASTM	USA	Steel and Tube
A791 Grade 25-4-4	ASTM	USA	Steel and Tube
A791 Grade 25-4-4	ASTM	USA	Steel and Tube

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.