

Material - ASTM A1001 Grade 5 Class A

Standard Specification for High Strength Steel Castings in Heavy Sections

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A1001 High Strength Steel Castings in Heavy Sections

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
-	-	-	Annealing or Hardening + Tempering	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	760 min.
-	-	-	Yield Strength in Mpa	620 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	36 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	34 min. @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA 216 WCB	ASME	USA	Casting
A757 A1Q	ASTM	USA	Casting
J03002	UNS	USA	Casting
1.0619	DIN	Germany	Casting
1.0619	EN	European Union	Casting
A660 WCB	ASTM	USA	Fusion Welding, Bending and Forming
SA 660 WCB	ASME	USA	Centrifugal Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.