

Material - ASTM A128 Grade B-2

Standard Specification for Steel Castings, Austenitic Manganese

Group - Ferrous Austenitic Manganese Steel Alloy

Sub Group - ASTM A128 / A128M Steel Castings, Austenitic Manganese

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	1.050 - 1.200	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	11.500 - 14.000		
Phosphorus	P %	0.070 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Z 120 M 12	AFNOR NF	France	Steel
BW10	BS	British	Casting
X 120 Mn 12	DIN	Germany	Steel
11OG13L	GOST	Russia	Casting
SCMnH1	JIS	Japan	Casting
G X 120 Mn 12	UNI	Italy	Casting
J91109	UNS	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.