

Material - ASTM A182 F 309H

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A182 F 309H Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Pipe and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.100	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	22.000 - 24.000		
Nickel	Ni %	12.000 - 15.000		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 485 min. Yield Strength in Mpa 205 min. Elongation in % 30 min. Reduction of Area in % 50 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S30908	ASTM	USA	Steel, Plate, Sheet and Strip
309	AMS	USA	Steel, Bar, Wire, Shape and Forging
309	SAE	USA	Steel, Bar, Wire, Shape and Forging
309 S 16	BS	British	Steel and Plates
STS 309S	KS	Korea	Steel, Plate, Sheet and Strip
SUH 309	JIS	Japan	Steel, Bar and Wire
30309	AISI	USA	Steel, Bar, Wire and Forging

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.