

Material - ASTM A217 Grade WC11

Standard Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A217 / A217M Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.210	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	1.000 - 1.500		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.450 - 0.650		
Copper	Cu %	0.350 max.	Mechanical Properties	
Aluminium	Al %	0.010 max.	Tensile Strength in Mpa	550 - 725
Vanadium	V %	0.030 max.	Yield Strength in Mpa	345 min.
Other	Ot %	1.000 max.	Elongation in %	18 min.
Iron	Fe %	Balance	Reduction of Area in %	45 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J11872	UNS	USA	Casting
SA-217 Grade WC11	ASME	USA	Casting
G 17 CrMo 5-5	AFNOR NF	France	Steel
A426 Grade CP11	ASTM	USA	Steel
621	BS	British	Plate
G S 17 CrMo 5-5	DIN	Germany	Casting
G S 17 CrMo 5-5	EN	European Union	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.