

Material - ASTM A240 UNS S30200

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Solution Annealing	
Silicon	Si %	0.750 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	8.000 - 10.000		
Nitrogen	N %	0.100 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	201 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A743 CF8	ASTM	USA	Casting
304	AISI	USA	Bar, Wire, Strip, Plate, Sheet and Forging
1.4308	DIN	Germany	Casting
1.4301	EN	European Union	Forging
304 S 11	BS	British	Bright Bars, Hot Rolled and Cold Rolled Coil
SUS 304	JIS	Japan	Hot Rolled Equal Leg Angles
08CH18N10	GOST	Russia	Pipes, Fittings, Bar, Sheet and Forging

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.