

Material - ASTM A240 UNS S32803

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.015 max.	Solution Annealing	
Silicon	Si %	0.550 max.		
Manganese	Mn %	0.500 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.0035 max.		
Chromium	Cr %	28.000 - 29.000		
Nickel	Ni %	3.000 - 4.000		
Molybdenum	Mo %	1.800 - 2.500		
Nitrogen	N %	0.020 max.	Mechanical Properties	
Niobium	Nb %	0.010 - 0.050	Tensile Strength in Mpa	600 min.
C + N	C % + N %	0.030 max.	Yield Strength in Mpa	500 min.
Iron	Fe %	Balance	Elongation in %	16 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	241 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S32803	UNS	USA	Steel
A176 S32803	ASTM	USA	Steel, Sheet, Plate and Strip
A959 S32803	ASTM	USA	Steel
SA-240 UNS S32803	ASME	USA	Steel
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.