

Material - ASTM A240 UNS S38815

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	5.500 - 6.500		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	13.000 - 15.000		
Nickel	Ni %	13.000 - 17.000		
Molybdenum	Mo %	0.750 - 1.500		
Copper	Cu %	0.750 - 1.500	Mechanical Properties	
Aluminium	Al %	0.300 max.	Tensile Strength in Mpa	540 min.
Iron	Fe %	Balance	Yield Strength in Mpa	255 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S38815	UNS	USA	Steel
A403 WP S38815	ASTM	USA	Steel and Pipe
A959 S38815	ASTM	USA	Steel
SA-240 S38815	ASME	USA	Steel
SA-249 S38815	ASME	USA	Steel
SA-312 S38815	ASME	USA	Steel
SA-479 S38815	ASME	USA	Steel

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.