

Material - ASTM A240 UNS S44626

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A240 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Annealing or Hardening + Tempering	
Silicon	Si %	0.750 max.		
Manganese	Mn %	0.750 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	25.000 - 27.000		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.750 - 1.500		
Nitrogen	N %	0.040 max.	Mechanical Properties	
Copper	Cu %	0.200 max.	Tensile Strength in Mpa	470 min.
Titanium	Ti %	0.200 - 1.000	Yield Strength in Mpa	310 min.
Iron	Fe %	Balance	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	217 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S44626	UNS	USA	Steel
XM-33	SAE	USA	Steel
A176 Type XM-33	ASTM	USA	Steel, Sheet, Plate and Strip
A268 TP XM-33	ASTM	USA	Steel and Tube
A959 Type XM-33	ASTM	USA	Steel
A731 Grade TP XM-33	ASTM	USA	Steel and Pipe
A791 Grade TP XM-33	ASTM	USA	Steel and Tube

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.