

Material - ASTM A268 29-4-2

Standard Specification for Seamless and Ferritic Stainless Steel Tubing for General Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A268 29-4-2 Seamless and Welded Ferritic Stainless Steel Tubing for General Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.200 max.		
Manganese	Mn %	0.300 max.		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	28.000 - 30.000		
Molybdenum	Mo %	3.500 - 4.200		
Nickel	Ni %	2.000 - 2.500	Mechanical Properties Tensile Strength in Mpa 550 min. Yield Strength in Mpa 415 min. Elongation in % 11 min. Reduction of Area in % - Hardness in HB 207 max. Impact in Joule -	
C+N	C % + N %	0.025 max.		
Nitrogen	N %	0.020 max.		
Copper	Cu %	0.150 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
S44800	UNS	USA	Plate, Sheet and Strip
SA-731 29-4-2	ASME	USA	Casting
A497 S44800	ASTM	USA	Plate, Bar and Forging
A511 29-4-2	ASTM	USA	Tube
A791 Grade 29-4-2	ASTM	USA	Plate, Sheet and Strip
SA-240 Type 29-4-2	ASME	USA	Plate, Sheet and Strip
A731 29-4-2	ASTM	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.