

Material - ASTM A297 GradeCT15C

Standard Specification for Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant for General Application

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A297/ A297M Steel Castings, Iron-Chromium and Iron-Chromium-Nickel, Heat Resistant for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.150	As - Cast	
Silicon	Si %	0.150 - 1.500		
Manganese	Mn %	0.150 - 1.500		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	19.000 - 21.000		
Nickel	Ni %	31.000 - 34.000		
Niobium	Nb %	0.500 - 1.500		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 435 min. Yield Strength in Mpa 170 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-351 CT15C	ASTM	USA	Casting
1.4859	DIN	Germany	Casting
G X 40NiCrSiNb 38-18	DIN	Germany	Casting
G X 10 NiCrNb 32-20	DIN	Germany	Casting
N08151	UNS	USA	Casting
N08004	UNS	USA	Casting
1.4849	DIN	Germany	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.