

Material - ASTM A351 CK3MCuN

Standard Specification for Castings, Austenitic, for Pressure-Containing Parts

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A351 / 351M Castings, Austenitic, for Pressure-Containing Parts

Application - Intended for Valves, Pumps, General Engineering, Automobile and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.200 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.500 - 20.500		
Nickel	Ni %	17.500 - 19.500		
Molybdenum	Mo %	6.000 - 7.000		
Copper	Cu %	0.500 -1.000		
Nitrogen	N %	0.180 - 0.240	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	260 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A743 CK3MCuN	ASTM	USA	Casting
SA-351 CKMCuN	ASME	USA	Casting
Z 4 CND 19.13 M	AFNOR NF	France	Casting
317 C 12	BS	British	Casting
422940	CSN	Czech Republic	Casting
J92810	UNS	USA	Casting
J93254	UNS	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.