

Material - ASTM A352 LC9

Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A352 / A352M Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.130 max.	Normalising + Tempering or Hardening + Tempering	
Silicon	Si %	0.450 max.		
Manganese	Mn %	0.900 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.500 max.		
Nickel	Ni %	8.500 - 10.000		
Molybdenum	Mo %	0.200 max.		
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.030 max.	Tensile Strength in Mpa	585 min.
Iron	Fe %	Balance	Yield Strength in Mpa	515 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	27 min. @ -196°C

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J31300	UNS	USA	Casting
SA-352 LC9	ASME	USA	Casting
B-136 Grade LC9	NMX	Maxico	Casting
A352 J31300	ASTM	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.