

Material - ASTM A352 LCB

Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A352 / A352M Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	Normalising + Tempering or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.500 max.		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.200 max.		
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.030 max.	Tensile Strength in Mpa	450 - 620
Iron	Fe %	Balance	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	24 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	18 min. @ -46°C

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J03003	UNS	USA	Casting
SA 352 LCB	ASME	USA	Casting
1.1156	DIN	Germany	Casting
GC24E	EN	European Union	Casting
1.1156	EN	European Union	Casting
1.0619	EN	European Union	Casting
1.0619	DIN	Germany	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.