

Material - ASTM A358 N08810

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A358 N08810 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.100	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	19.000 - 23.000		
Nickel	Ni %	30.000 - 35.000		
Titanium	Ti %	0.150 - 0.600	Mechanical Properties	
Aluminium	Al %	0.150 - 0.600		
Copper	Cu %	0.750 max.		
Iron	Fe %	39.500 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Tensile Strength in Mpa	
-	-	-	Yield Strength in Mpa	
-	-	-	Elongation in %	
-	-	-	Reduction of Area in %	
-	-	-	Hardness in BHN	
-	-	-	Impact in Joule	

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS N08800	ASTM	USA	Steel, Plate, Sheet and Strip
N08800	UNS	USA	Steel
A358 N08800	ASTM	USA	Steel
A959 Type800	ASTM	USA	Steel
1.4958	EN	European Union	Flat and Steel
1.4958	DIN	Germany	Flat and Steel
A959 N08811	ASTM	USA	Steel

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.