

Material - ASTM A487 10(B)

Standard Specification for Steel Castings Suitable for Pressure Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A487 / AA87M Steel Castings Suitable for Pressure Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.800 max.		
Manganese	Mn %	0.600 - 1.000		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.550 - 0.900		
Nickel	Ni %	1.400 - 2.000		
Molybdenum	Mo %	0.200 - 0.400		
Copper	Cu %	0.500 max.		
			Mechanical Properties	
Vanadium	V %	0.030 max.	Tensile Strength in Mpa	860 min.
Tungsten	W %	0.100 max.	Yield Strength in Mpa	690 min.
Other	Ot %	0.600 max.	Elongation in %	15 min.
Iron	Fe %	Balance	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J23015	UNS	USA	Casting
A487 10A	ASTM	USA	Casting
SA-487 10A	ASME	USA	Casting
SA-487 10B	ASME	USA	Casting
A487 9Q	ASTM	USA	Casting
J23055	UNS	USA	Casting
4330	AISI	USA	Forging , Bar, Wire and Shape

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.