

Material - ASTM A608 Grade HN 40

Standard Specification for Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 608/A 608M Centrifugally Cast Iron-Chromium-Nickel High-Alloy Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 - 0.450	As - Cast	
Silicon	Si %	0.500 - 2.000		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	19.000 - 23.000		
Molybdenum	Mo %	0.050 max.		
Nickel	Ni %	23.000 - 27.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 435 min. Yield Strength in Mpa - Elongation in % 8 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J94213	UNS	USA	Casting
J94214	UNS	USA	Casting
SCH 19	JIS	Japan	Casting
A297 Grade HN	ASTM	USA	Casting
SCH 19	JIS	Japan	Casting
IS 4522 Grade 11	DIN	Germany	Casting
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.