

Material - ASTM A731 CA 6 NM

Standard Specification for Castings, Seamless and Ferritic Stainless Steel Pipe

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A731 CA 6 NM Seamless and Ferritic Stainless Steel Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.	Hardening + Tempering	
Silicon	Si %	0.060 max.		
Manganese	Mn %	0.050 - 1.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.000		
Molybdenum	Mo %	0.500 - 1.000		
Ni+Cu	Ni% + Cu%	3.500 - 5.500		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	795 min.
-	-	-	Yield Strength in Mpa	620 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-731 CA6NM	ASME	USA	Casting
A356 CA6NM	ASTM	USA	Casting
A487 CA6NM	ASTM	USA	Casting
SA-352 Grade CA6NM	ASME	USA	Casting
SA-487 Grade CA6NMA	ASME	USA	Casting
SA-487 Grade CA6NMB	ASME	USA	Casting
SA-487 Class CA6NM	ASME	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.