

Material - ASTM A731 TP XM-27

Standard Specification for Castings, Seamless and Welded Ferritic Stainless Steel Pipe

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A731 TP XM-27 Seamless and Welded Ferritic Stainless Steel Pipe

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.400 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	25.000 - 27.500		
Molybdenum	Mo %	0.750 - 1.500		
Nitrogen	N %	0.015 max.	Mechanical Properties Tensile Strength in Mpa 450 min. Yield Strength in Mpa 275 min. Elongation in % 20 min. Reduction of Area in % 45 min. Hardness in BHN - Impact in Joule -	
Niobium	Nb %	0.050 - 0.200		
Copper	Cu %	0.200 max.		
Ni+Cu	Ni% + Cu%	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-731 TP XM-27	ASME	USA	Casting
A176 Type XM-27	ASTM	USA	Plate, Sheet and Strip
A240 Type XM-27	ASTM	USA	Plate, Sheet and Strip
A276 XM-27	ASTM	USA	Bar and Shapes
S44627	UNS	USA	Plate, Sheet and Strip
SM-27	SAE	USA	Plate, Sheet and Strip
SA-276 XM-27	ASME	USA	Bar and Shape

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.