

Material - ASTM A732 12Q

Standard Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A732 / A7323M Casting, Investment, Carbon and Low Alloy Steel for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.450 - 0.550	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.200 - 0.800		
Manganese	Mn %	0.650 - 0.950		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.800 - 1.100		
Nickel	Ni %	0.500 max.		
Mo + W	Mo% + W%	0.100 max.		
Vanadium	V %	0.150 min.	Mechanical Properties	
Copper	Cu %	0.500 max.	Tensile Strength in Mpa	1310 min.
other	Ot %	1.000 max.	Yield Strength in Mpa	1172 min.
Iron	Fe %	Balance	Elongation in %	4 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
6150	AISI	USA	Ingot, Rolling, Bar, Strip and Tube
6150	SAE	USA	Steel and Bar
6150	AMS	USA	Steel and Bar
J15048	UNS	USA	Casting
6150	AS	Australia	Steel
K15047	UNS	USA	Steel
K15048	UNS	USA	Steel

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.