

Material - ASTM A732 13Q

Standard Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A732 / A7323M Casting, Investment, Carbon and Low Alloy Steel for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.250	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.200 - 0.800		
Manganese	Mn %	0.650 - 0.950		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.400 - 0.700		
Nickel	Ni %	0.400 - 0.700		
Molybdenum	Mo %	0.150 - 0.250	Mechanical Properties Tensile Strength in Mpa 724 min. Yield Strength in Mpa 586 min. Elongation in % 10 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Copper	Cu %	0.500 max.		
Tungsten	W %	0.100 max.		
other	Ot %	1.000 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
8620	AISI	USA	Steel
8620	SAE	USA	Steel, Bar, Forging and Tube
8620	AMS	USA	Steel
J12048	UNS	USA	Casting
J13047	UNS	USA	Casting
A487 4A	ASTM	USA	Casting
A487 4B	ASTM	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.