

Material - ASTM A732 4A

Standard Specification for Castings, Investment, Carbon and Low Alloy Steel for General Application, and Cobalt Alloy for High Strength at Elevated Temperatures

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A732 / A7323M Casting, Investment, Carbon and Low Alloy Steel for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.450 - 0.550	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.200 - 1.000		
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Copper	Cu %	0.500 max.		
Tungsten	W %	0.100 max.		
Other	Ot %	0.600 max.	Mechanical Properties Tensile Strength in Mpa 621 min. Yield Strength in Mpa 345 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1050	AISI	USA	Forging, Bar, Wire, and Shape
1606	SS	Sweden	Casting
50 CD 4 M	AFNOR NF	France	Casting
5152	SAE	USA	Steel
735 A51	BS	British	Hot Formed Spring
C3	MSZ	Hungary	Steel
C48GW-N-A	JIS	Japan	Forging

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.