

Material - ASTM A743 CA 15M

Standard Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A743 / A743M Casting, Iron-Chromium-Nickel, corrosion Resistant Casting, for General Application

Application - Intended for Valves, Pumps, General Engineering, Automobile and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Annealing or Hardening + Tempering	
Silicon	Si %	0.650 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	11.500 - 14.000		
Nickel	Ni %	1.000 max.		
Molybdenum	Mo %	0.150 - 1.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	620 min.
-	-	-	Yield Strength in Mpa	450 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardness in HB	241 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A487 CA 15M	ASTM	USA	Casting
SA-487 Grade CA 15M	ASME	USA	Casting
SA-487 Grade CA 15MA	ASME	USA	Casting
J91151	UNS	USA	Casting
410	SAE	USA	Bar, Wire, Shape and Forging
A 217 CA 15	ASTM	USA	Casting
A743 CA 15	ASTM	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.