

Material - ASTM A743 CA28MWV

Standard Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A743 / A743M Casting, Iron-Chromium-Nickel, corrosion Resistant Casting, for General Application

Application - Intended for Valves, Pumps, General Engineering, Automobile and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.280	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	0.500 - 1.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.000 - 12.500		
Nickel	Ni %	0.500 - 1.000		
Molybdenum	Mo %	0.900 - 1.250		
Vanadium	V %	0.200 - 0.300	Mechanical Properties	
Tungsten	W %	0.900 - 1.250	Tensile Strength in Mpa	965 min.
Iron	Fe %	Balance	Yield Strength in Mpa	760 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	24 min.
-	-	-	Hardness in HB	302 - 352 or 269 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
422	AISI	USA	Bar, Wire, Shape and Forging
1.4935	DIN	Germany	Casting
SUH 616	JIS	Japan	Bar and Wire
20 VNiMoCr 120	STAS	Romania	Casting
S42100	UNS	USA	Casting
X 20 CrMoWV 12-1	DIN	Germany	Casting
A176 Type 422	ASTM	USA	Plate, Sheet and Strip

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.