

Material - ASTM A743 CF16Fa

Standard Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for General Application

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A743 / A743M Casting, Iron-Chromium-Nickel, corrosion Resistant Casting, for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.160 max.	Solution Annealing	
Silicon	Si %	2.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.200 - 0.400		
Chromium	Cr %	18.000 - 21.000		
Nickel	Ni %	9.000 - 12.000		
Molybdenum	Mo %	0.400 - 0.800		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
3444 Grade 6A	IS	India	Casting
CF-16Fa	NBR	Brazil	Casting
CF-16Fa	NMX	Maxico	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.