

## Material - ASTM A747 Grade CB7Cu-1 (H1150M)

Standard Specification for Steel Castings, Stainless, Precipitation Hardening

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A747 / A747M Steel Castings, Stainless, Precipitation Hardening

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

| Chemical Composition |      |               | Heat Treatment                                                                                                                                                                         |  |
|----------------------|------|---------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|
| Carbon               | C %  | 0.070 max.    | Normalising or Annealing or Hardening + Tempering                                                                                                                                      |  |
| Silicon              | Si % | 1.000 max.    |                                                                                                                                                                                        |  |
| Manganese            | Mn % | 0.700 max.    |                                                                                                                                                                                        |  |
| Phosphorus           | P %  | 0.035 max.    |                                                                                                                                                                                        |  |
| Sulphur              | S %  | 0.030 max.    |                                                                                                                                                                                        |  |
| Chromium             | Cr % | 15.500 17.700 |                                                                                                                                                                                        |  |
| Nickel               | Ni % | 3.600 - 4.600 |                                                                                                                                                                                        |  |
| Copper               | Cu % | 2.500 - 3.200 |                                                                                                                                                                                        |  |
| Niobium              | Nb % | 0.150 - 0.350 |                                                                                                                                                                                        |  |
| Nitrogen             | N %  | 0.050 max.    |                                                                                                                                                                                        |  |
| Iron                 | Fe % | Balance       | <b>Mechanical Properties</b><br>Tensile Strength in Mpa -<br>Yield Strength in Mpa -<br>Elongation in % -<br>Reduction of Area in % -<br>Hardness in BHN 310 max.<br>Impact in Joule - |  |
| -                    | -    | -             |                                                                                                                                                                                        |  |
| -                    | -    | -             |                                                                                                                                                                                        |  |
| -                    | -    | -             |                                                                                                                                                                                        |  |
| -                    | -    | -             |                                                                                                                                                                                        |  |
| -                    | -    | -             |                                                                                                                                                                                        |  |

| Cross Reference Table |          |                |                              |
|-----------------------|----------|----------------|------------------------------|
| Material              | Standard | Country        | Grade Belong to the Industry |
| J92180                | UNS      | USA            | Casting                      |
| SA-747 CB7Cu-1        | ASME     | USA            | Casting                      |
| 17-4PH                | SAE      | USA            | Steel                        |
| Z 7 CNU 17-04         | AFNOR NF | France         | Steel                        |
| 5622                  | AMS      | USA            | Bar, Wire, Tube and Forging  |
| X 5 CrNiCuNb 16-4     | DIN      | Germany        | Steel                        |
| X 5 CrNiCuNb 16-4     | EN       | European Union | Forging                      |

For any further inquiries, please do not hesitate to contact us. You may visit our website at [AMTECH TECHNOCAST PVT. LTD.](http://AMTECH TECHNOCAST PVT. LTD.), call us at [+91 9879817994](tel:+919879817994), or email us at [manish@amtechtechnocast.com](mailto:manish@amtechtechnocast.com)

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.