

Material - ASTM A890 3A

Standard Specification for Castings, Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A890 / A890M Iron-Chromium-Nickel-Molybdenum Corrosion-Resistant, Duplex (Austenitic/Ferritic) for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	24.000 - 27.000		
Nickel	Ni %	4.000 - 6.000		
Molybdenum	Mo %	1.750 - 2.500		
Nitrogen	N %	0.150 - 0.250	Mechanical Properties	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Tensile Strength in Mpa	655 min.
			Yield Strength in Mpa	450 min.
			Elongation in %	25 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A995 3A	ASTM	USA	Casting
J93371	UNS	USA	Casting
A240 UNS 32900	ASTM	USA	Steel, Sheet, Plate and Strip
A240 UNS S32950	UNS	USA	Steel, Sheet, Plate and Strip
25Cr5NiMoN	ASTM	USA	Casting
CD6MN	ASTM	USA	Casting
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.