

Material - ASTM A895 Type 420F

Standard Specification for Free-Machining Stainless Steel Plate, Sheet and Strip

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A895 Type 420F Free-Machining Stainless Steel Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.400	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.250 max.		
Phosphorus	P %	0.060 max.		
Sulphur	S %	0.150 min.		
Chromium	Cr %	12.000 - 14.000		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.600 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 690 min. Yield Strength in Mpa 485 min. Elongation in % 12 min. Reduction of Area in % - Hardness in HB 262 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
420F	AISI	USA	Bar, Wire, Shapes and Forging
J9154	UNS	USA	Casting
A959 Type 420F	ASTM	USA	Bar, Wire, Shapes and Forging
A 582 Type 420F	ASTM	USA	Bar and Forging
SUS 420F	JIS	Japan	Bar and Forging
S 42020	UNS	USA	Casting
A743 CA40F	ASTM	USA	Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.