

Material - ASTM B 164 N04405

Standard Specification for Nickel-Copper Alloy Rod, Bar and Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 164 N04405 Nickel-Copper Alloy Rod, Bar and Wire

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Rod, Bar and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.000 max.		
Copper	Cu %	28.000 - 34.000		
Sulphur	S %	0.025 - 0.060		
Iron	Fe %	2.500 max.		
Nickel	Ni %	63.000 min.		
-	-	-	Mechanical Properties Tensile Strength in Mpa 480 - 758 Yield Strength in Mpa 170 min. Elongation in % 8 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N04405	UNS	USA	Bar and Forging
SB-164 N04405	ASME	USA	Rod, Bar and Wire
Monel Alloy R-405	Gravity	India	Rod, Bar and Wire
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.