

Material - ASTM B 167 N06025

Standard Specification for Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Seamless Pipe and Tube

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 167 N06025 Nickel-Chromium-Iron Alloys and Nickel-Chromium-Cobalt-Molybdenum Alloy Seamless Pipe and Tube

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.250	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.150 max.		
Copper	Cu %	0.100 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	24.000 - 26.000		
Iron	Fe %	8.000 - 11.000		
Aluminium	Al %	1.800 - 2.400		
Titanium	Ti %	0.100 - 0.200	Mechanical Properties	
Phosphorus	P %	0.020 max.	Tensile Strength in Mpa	680 - 860
Zirconium	Zr %	0.010 - 0.100	Yield Strength in Mpa	270 min.
Yttrium	Y %	0.050 - 0.120	Elongation in %	30 min.
Nickel	Ni %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 163 N06025	ASTM	USA	Tube
B 166 N06025	ASTM	USA	Rod, Bar and Wire
B 168 N06025	ASTM	USA	Plate, Sheet and Strip
B 564 N06025	ASTM	USA	Forging
B 516 N06025	ASTM	USA	Tube
B 517 N06025	ASTM	USA	Pipe
B 462 N06025	ASTM	USA	Pipe and Valve

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.