

Material - ASTM B 240 AC41A

Standard Specification For Zinc and Zinc Alloy Castings

Group - Non-Ferrous Zinc Alloys

Sub Group - ASTM B 240 AC41A Zinc and Zinc Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.900 - 4.300	As-Cast	
Copper	Cu %	0.700 - 1.100		
Magnesium	Mg %	0.035 - 0.060		
Lead	Pb %	0.004 max.		
Cadmium	Cd %	0.003 max.		
Tin	Sn %	0.0015 max.		
Iron	Fe %	0.035 max.		
Nickel	Ni %	0.020 max.		
Silicon	Si %	0.035 max.		
Zinc	Zn %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	330 min.
-	-	-	Yield Strength in Mpa	250 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	92 min.
-	-	-	Impact in Joule	58 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP5	DIN	Germany	Casting
Alloy B	BS	British	Casting
G-ZnAl4Cu1	UNI	Italy	Ingot
ZnAl4Cu1	UNE	Spain	Ingot
ZnAl4Cu1	NS	Norway	Ingot
ZnAl4Cu1	SS	Sweden	Ingot
2.2141	DIN	Germany	Ingot and Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.