

Material - ASTM B 26 712.0

Standard Specification for Aluminium Alloy Sand Casting

Group - Non-Ferrous Aluminium Alloy

Sub Group - ASTM B 26 Aluminium Alloy Sand Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.250 max.	As-Cast	
Iron	Fe %	0.500 max.		
Magnesium	Mg %	0.500 - 0.650		
Manganese	Mn %	0.100 max.		
Silicon	Si %	0.300 max.		
Titanium	Ti %	0.150 - 0.250		
Zinc	Zn %	5.000 - 6.500		
Chromium	Cr %	0.400 - 0.600		
Other	Ot%	0.200 max.		
Aluminium	Al %	Balance	Mechanical Properties Tensile Strength in Mpa 235 min. Yield Strength in Mpa 170 min. Elongation in % 4 min. Reduction of Area in % - Hardness in HB 75 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM31	BS	British	Ingot and Casting
712.0	AA	USA	Casting
Al Zn5Mg	ISO	International	Ingot and Casting
712.0	SAE	USA	Casting
BA701	AS	Australia	Ingot and Casting
L-2710	UNE	Spain	Ingot and Casting
A-Z5G	AFNOR NF	France	Ingot and Casting

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.