

Material - ASTM B 335 N10675

Standard Specification for Nickel-Molybdenum Alloy Rod

Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B 335 N10675 Nickel-Molybdenum Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Rod

Chemical Composition		
Carbon	C %	0.010 max.
Silicon	Si %	0.100 max.
Manganese	Mn %	3.000 max.
Phosphorus	P %	0.030 max.
Cobalt	Co %	3.000 max.
Sulphur	S %	0.010 max.
Chromium	Cr %	1.000 - 3.000
Iron	Fe %	1.000 - 3.000
Molybdenum	Mo %	27.000 - 32.000
Vanadium	V %	0.200 max.
Aluminium	Al %	0.500 max.
Niobium	Nb %	0.200 max.
Copper	Cu %	0.200 max.
Tantalum	Ta %	0.200 max.
Titanium	Ti %	0.200 max.

Chemical Composition		
Tungsten	W %	3.000 max.
Zirconium	Zr %	0.100 max.
Ni + Mo	Ni% + Mo%	54.000 - 68.000
Nickel	Ni %	65.000 min.
-	-	-
Heat Treatment		
As-Cast or Annealing or Age Hardning		
Mechanical Properties		
Tensile Strength in Mpa	760 min.	
Yield Strength in Mpa	350 min.	
Elongation in %	40 min.	
Reduction of Area in %	-	
Hardness in BHN	-	
Impact in Joule	-	

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 333 N10675	ASTM	USA	Plate, Sheet and Strip
B 564 N10675	ASTM	USA	Forging
B 472 N10675	ASTM	USA	Bar
B 619 N10675	ASTM	USA	Pipe
B 622 N10675	ASTM	USA	Pipe and Tube
B 626 N10675	ASTM	USA	Tube
-	-	-	-

For any further inquiries, please do not hesitate to contact us. You may visit our website at AMTECH TECHNOCAST PVT. LTD., call us at [+91 9879817994](tel:+919879817994), or email us at manish@amtechtechnocast.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.